



Technical Report: (9615) 236-0157
Date Received: AUGUST 24, 2015

AUGUST 27, 2015
Page 1 of 4

NGUYEN VO HOAN KIM
CN DNTN SAN XUAT, THUONG MAI KEO DAN VA NHUA TONG HOP NGHIEP PHAT
24/15 KP BINH PHUOC B, P.BINH CHUAN, TX. THUAN AN, BINH DUONG

Sample Description:	SON DAC CHUNG BONG TRONG TREN KIM LOAI (DONG - BRASS, COPPER) - BDC01		
Vendor:	CN DNTN SAN XUAT, THUONG MAI KEO DAN VA NHUA TONG HOP NGHIEP PHAT	Sample Size:	/
Manufacturer:	SON HOA VIET	VPN:	/
Buyer:	/	SKN/SKU No.:	/
Agent:	/	PO No.:	/
Labeled Age Grade:	/	Ref #:	/
Appropriate Age Grade:	/	Country of Origin:	/
Client Specified Age Grade:	/	Assortment No.:	/
Tested Age Grade:	/	Department No.:	/
UPC Code:	/	ITEM#:	/
Phase of Production:	/	Date of Production:	/
Color:	/	Model/Style#:	/
Program:	/	Country of Destination:	/
Previous No:	N/A		

TEST:

- Resistance To Corrosion

EXECUTIVE SUMMARY:

The sample(s) MEETS the following requirement(s):

- The requirement of ASTM B117-11 modified / CPSD- HL- 01010-MTHD, Resistance to Corrosion.



CN DNTN SAN XUAT, THUONG MAI KEO DAN VA NHUA TONG HOP NGHIEP PHAT
Technical Report: **(9615) 236-0157**
AUGUST 27, 2015
Page 2 of 4

BVCPS Contact information for this report.

Technical questions:

Technical questions: Terry Nguyen, Tel: 848-37421-604 ~ 6; email: terry.nguyen@vn.bureauveritas.com

Technical questions: Ron Nguyen, Tel: 848-37421-604 ~ 6; email: ron.nguyen@vn.bureauveritas.com

Concerns About Billing and General Inquiries:

Primary Contact: Ryan Nguyen, Tel: 848-37421-604 ~ 6; email: ryan.nguyen@vn.bureauveritas.com

Back-up Contact: Abby Pham, Tel: 848-37421-604 ~ 6; email: abby.pham@vn.bureauveritas.com

BUREAU VERITAS CONSUMER PRODUCTS SERVICES (VN) LTD.

**TERRY NGUYEN
AUTHORIZE REPORT APPROVER**



RESULT(S):

Evaluation	Citation / Method	Criteria	Results	Rating
Resistance to corrosion	ASTM B117-11 modified / CPSD - HL – 01010-MTHD	[Applicable to samples / sample components constructed of metal or samples with metallic coatings that can be exposed to the environment] Shall withstand 24 hours in 5 % salt spray (fog) with no noticeable oxidation / corrosion / visual changes. Modification = 5 % salt spray (fog).	M (No Visual Changes)	PASS

Results Key:

M	Meets	NM	Does Not Meet
NA	Not Applicable	NT	Not Tested
C	Claimed	R	Recorded

